

## PRODUCT DATA SHEET

Date: 05/09/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

iGOTM Semi Gloss \*\* ATPTM \*\* 40# liner

Item#: 0042708

Recommended Print Type(s) to Test  Durst US (UV inkjet)  HP Indigo®	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
	Troy, Ohio	2.5 K	3"	3"
	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	3"	3"
	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Ontario, CA	5 K	3"	3"
	Ontario, CA	10 K	4"	3"

Facestock: iGOTM Semi Gloss This glossy, white HP Indigo-ready 55# Semi Gloss is top-coated for excellent adhesion of HP Indigo liquid ink to the facestock.

This facestock is not recommended for wet applications.

**Typical Value** 

Basis Weight: 55 #/3300 ft<sup>2</sup> Caliper: 3.2 mils Tensile MD/CD: 25 / 17 Gloss: 62% Tear MD/CD: 45 / 49 grams

89%

Opacity:

Parker Print: 1.0 microns

87% Brightness:

Adhesive: ATP<sup>TM</sup> An all-temperature permanent acrylic adhesive suitable for a wide variety of

applications with paper facestocks providing exceptional converting

characteristics that allow stripping of intricate die patterns as well as wide-web,

high-speed processing.

**Typical Value** 

Coat Weight: 15 #/3300 ft<sup>2</sup> Coat Weight: 22.2 grams/m<sup>2</sup>

.6 mils Caliper: Adhesion to Stainless Steel, oz. (90° Peel): 20 Loop Tack, oz.: 41

-65 to 200 °F Service Temperature:

Minimum Application Temperature: -20 °F Shear (1000g): 61 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

Basis Weight:  $41 \#/3000 \text{ ft}^2$  Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

**Total Product Caliper:** 6.3 mils

Product Basis Weight Per MMSI: 242.32 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023